

Test Report

Client : Flashbay Electronics Huizhou
Building2, Jixun Industrial Park, Xinjiao, Dong'ao Village, Shatian
Town, Huiyang District, Huizhou City, Guangdong Province, P.R.
China

Sample Description : Foodware
Model No. : Snacks (SNK)
Reference Information^Δ : Refer to Annex

The information and sample(s) above were submitted and identified by or on behalf of the client.

Sample Received : 2026-04-08
Testing Period : 2026-04-08 to 2026-04-29

<u>Test Requested</u>		<u>Result</u>
1.	U.S. 21 CFR F.D.A. Regulation Part 177.1520 Clause 1.1a and 1.1b on polypropylene	PASS
2.	U.S. F.D.A. Regulation 21 CFR Part 177.2600 on rubber articles intended for repeated use, Section (e) and (f)	PASS





Signed for and on behalf of
DEKRA Testing and Certification (Shanghai) Ltd., Guangzhou branch



Devin Ai
Approver

Picture of Sample Tested

Tested Sample Description:

No.	Specimen Description	Material(s) (claimed by applicant)	Photo
1.	Seal ring	Silicone (Translucence)	
2.	Body	Silicone (Black)	
3.	Lid	PP (Translucence)	
4.	Fork	PP (Black)	

TEST RESULTS

1. U.S. 21 CFR F.D.A. Regulation Part 177.1520 Clause 1.1a and 1.1b on polypropylene

With reference to the U.S. Food and Drug Administration 21 CFR Part 177.1520 Clause 1.1a and 1.1b.

	Parameter	Result		MDL	Limit
		(3)	(4)		
a)	Density	0.897	0.905	--	0.880-0.913
b)	Melting Point (°C)	164.2	176.3	--	160-180 (1.1a) 150-180 (1.1b)
c)	Maximum extractable fraction in n-hexane, % (w/w)	<0.5	<0.5	0.5	6.4
d)	Maximum extractable fraction in xylene, % (w/w)	0.99	3.59	0.5	9.8

Remark:

1. % = Percentage
2. MDL = Method Detection Limit

2. U.S. F.D.A. Regulation 21 CFR Part 177.2600 on rubber articles intended for repeated use, Section (e) and (f)


With reference to the U.S. Food and Drug Administration 21 CFR Part 177.2600 - rubber articles intended for repeated use, Section (e) and (f).

	Parameter	Test condition	Result (mg/in ²)		MDL (mg/in ²)	Limit (mg/in ²)
			(1)	(2)		
(a)	Total extractives in water	Reflux temperature, first 7 hours	0.4	0.5	0.20	20
		Reflux temperature, succeeding 2 hours	<0.20	<0.20	0.20	1
(b)	Total extractives in n-hexane	Reflux temperature, first 7 hours	12.9	8.7	0.20	175
		Reflux temperature, succeeding 2 hours	0.6	0.4	0.20	4

Remark:

1. mg/in² = Milligram per square inch

Annex



[△] The reference model information is provided by the client and claimed that the identical materials and/or construction as the tested samples are used. The samples displayed here are not tested samples and are for reference only DEKRA Testing and Certification (Shanghai) Ltd., Guangzhou branch takes no liability for information validation.

---End of Report---

This document is issued subject to the company's General Terms and Conditions available at <https://www.dekra.com.cn/en/terms-and-conditions/>. Unless otherwise stated, the test results refer exclusively to the samples tested in this report. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into consideration. DEKRA declines any responsibility with information provided and/or deviations required by the client that may affect the validity of test results. This report can only be reproduced in full and with written approval of the test laboratory. If you have any comment on the test results, please contact us in writing within 15 days after the issuance of this report. The test results shall not be used for propaganda without permission of the test laboratory. This report is not to be used for social proof function in China market.